



**Location: 72 South Main St.
Acushnet, MA 02743**

Phone: 508-992-3542

FAX: 508-994-9503

**Material: 1 1/2" Dense
Graded Base**

Sieve Size		% Passing
Metric	US Customary	
50.0 mm	2"	100
37.5 mm	1 1/2"	100
25.0 mm	1"	93
19.0 mm	3/4"	73
12.5 mm	1/2"	55
9.5 mm	3/8"	43
4.75 mm	#4	35
2.36 mm	#8	21
1.18 mm	#16	16
0.600 mm	#30	13
0.300 mm	#50	11
0.150 mm	#100	9
0.075 mm	#200	6
Physical Properties		
Maximum Dry Unit Weight (lbs/ft ³)		150.3 *
Optimum Moisture (%)		5.7

* Value has been adjusted to include +3/4" aggregate

Notes:

- 1) Testing in accordance with ASTM D-422.
ASTM D-1557 Laboratory Compaction Characteristics of Soil Using Modified Effort (Method "C").
- 2) All testing performed under the direct supervision of NETTCP certified Soil and Aggregate Technician.
- 3) Testing performed in P.J. Keating's laboratory meeting state specifications.
- 4) Additional information can be provided upon request.

NOTE: Maximum dry unit weight reported for informational purposes only, testing should be performed on the actual material supplied to determine project in-place density.