



**Location: 72 South Main St.
Acushnet, MA 02743**

Phone: 508-992-3542

FAX: 508-994-9503

Material: 1" K-RAP BASE

Sieve Size		% Passing
Metric	US Customary	
25.0 mm	1"	99
19.0 mm	3/4"	95
12.5 mm	1/2"	86
9.5 mm	3/8"	79
4.75 mm	#4	59
2.36 mm	#8	49
1.18 mm	#16	38
0.600 mm	#30	26
0.300 mm	#50	20
0.150 mm	#100	14
0.075 mm	#200	8.8
	% Asphalt	3.1
Physical Properties		

Notes:

- 1) Testing in accordance with C-136/T-27 Sieve Analysis of Fine and Coarse Aggregate,
- 2) All testing performed under the direct supervision of NETTCP certified Soil and Aggregate Technician.
- 3) Testing performed in P.J. Keating's laboratory meeting state specifications.
- 4) Additional information can be provided upon request.