



**Location: 998 Reservoir Rd.
Lunenburg, MA 01462**

Phone: 978-582-9931

FAX: 978-528-7130

Material: 3/8" Crushed Stone

Sieve Size		% Passing
Metric	US Customary	
12.5 mm	1/2"	100
9.5 mm	3/8"	88
4.75 mm	#4	15
2.36 mm	#8	1
1.18 mm	#16	1
0.075 mm	#200	0.4
Physical Properties		
Bulk Specific Gravity		2.710
Effective Specific Gravity		2.726
Apparent Specific Gravity		2.754
Absorption (%)		0.6
Dry Unit Weight (lbs/ft ³)		89.3
Sodium Soundness Loss (%)		0.8
LA Abrasion Loss (%)		23.8
Flat & Elongated 5:1 (%)		2
Fractured Faces (1 / 2)		100 / 100

Notes:

- 1) Testing in accordance with C-136/T-27 Sieve Analysis of Fine and Coarse Aggregate, T-85 Specific Gravity and Absorption of Coarse Aggregate, T-104 Soundness of Aggregate by Use of Sodium Sulfate or Magnesium Sulfate, T-96 Resistance to Degredation of Small-Size Coarse Aggregate by Abrasion and Impact in the Los Angeles Machine, D-4791 Flat or Elongated Particles in Coarse Aggregate.
- 2) All testing performed under the direct supervision of NETTCP a certified Technician.
- 3) Testing performed in P.J. Keating's laboratory meeting state specifications.
- 4) Additional information can be provided upon request.