



**Location: 998 Reservoir Rd.  
Lunenburg, MA01462**

**Phone: 978-582-9931  
FAX: 978-582-7130**

**Material: K - Pac**

Sieve Size		% Passing
Metric	US Customary	
9.5 mm	3/8"	100
4.75 mm	#4	99
2.36 mm	#8	91
1.18 mm	#16	64
0.600 mm	#30	43
0.300 mm	#50	27
0.150 mm	#100	18
0.075 mm	#200	15.1

**Notes:**

- 1) Testing in accordance with C-136/T-27 Sieve Analysis of Fine and Coarse Aggregate  
C-117/T-11 Materials Finer Than No. 200 Sieve in Mineral Aggregates by Washing
- 2) All testing performed under the direct supervision of NETTCP certified Soil and Aggregate Technician.
- 3) Testing performed in P.J. Keating's laboratory meeting state specifications.
- 4) Additional information can be provided upon request.