



**Location: 875 Phenix Avenue
Cranston, RI. 02921**

Phone: 401-942-7300

FAX: 401-943-2780

**Material: 3/8" Crushed Stone
Washed**

Sieve Size		% Passing
Metric	US Customary	
12.5 mm	1/2"	100
9.5 mm	3/8"	91
4.75 mm	#4	24
2.36 mm	#8	4
1.18 mm	#16	2
0.075 mm	#200	0.8
Physical Properties		
Bulk Specific Gravity		2.651
Effective Specific Gravity		2.672
Apparent Specific Gravity		2.707
Absorption (%)		0.8
Loose Dry Unit Weight (pcf)		97.8
Rodded Dry Unit Weight (pcf)		108.2
Sodium Soundness Loss (%)		0.8
LA Abrasion Loss (%)		24.1 (C)
Flat & Elongated 5:1 (%)		0
Uncompacted Voids (%)		52.9

Notes:

- 1) Testing in accordance with C-136/T-27 Sieve Analysis of Fine and Coarse Aggregate, T-85 Specific Gravity and Absorption of Coarse Aggregate, T-19 Bulk Density ("Unit Weight") Voids in Aggregates, T-104 Soundness of Aggregate by Use of Sodium Sulfate or Magnesium Sulfate, T-96 Resistance to Degredation of Small-Size Coarse Aggregate by Abrasion and Impact in the Los Angeles Machine, D-4791 Flat or Elongated Particles in Coarse Aggregate.
- 2) All testing performed under the direct supervision of NETTCP a certified Technician.
- 3) Testing performed in P.J. Keating's laboratory meeting state specifications.
- 4) Additional information can be provided upon request.