



**Location: 875 Phenix Ave
Cranston, RI 02921**

Phone: 401-942-7300

FAX: 401-943-2780

Material: Graded Base

Sieve Size		% Passing
Metric	US Customary	
25.0 mm	1"	100
19.0 mm	3/4"	97
12.5 mm	1/2"	94
9.5 mm	3/8"	85
4.75 mm	#4	62
2.36 mm	#8	45
1.18 mm	#16	38
0.600 mm	#30	31
0.300 mm	#50	22
0.150 mm	#100	15
0.075 mm	#200	11
Physical Properties		
Maximum Dry Unit Weight (lbs/ft ³)		145.8
Optimum Moisture (%)		5.3

Notes:

- 1) Testing in accordance with ASTM D422, "Standard Test Method for Particle-Size Analysis of Soils"
ASTM D1557, "Standard Test Method for Laboratory Compaction Characteristics of Soil Using Modified Effc

ort."